


60 w

Monocrystalline Solar Panel

Features


- •+/- 3% power tolerance;
- Quality supervision procedure is strictly implemented and test result of detailed current and voltage is supplied;
- Glass have self-cleaning ability, reducing the probability of generating efficiency cause by dust;
- Low working temperature of standard battery and excellent dim light property;
- All the solar panels have passed the test of mechanical loading, able to resist against the abominable and high-load working environment;
- Able to supply multi-specification and high-quality solar panels with an output power of 2w-300w, suitable for on/off grid applications;
- Many international certifications and tests have been passed;
- 25-year output power guarantee period, 5-year product quality guarantee period.










SA60-3672









Electrical Characteristics

Туре	SA50-36/72	SA55-36/72	SA60-36/72	
Maximum power (Wp)	50Wp	55Wp	60Wp	
Maximum power voltage (V)	18.00	18.00	18.00	
Maximum power current (A)	2.78	3.05	3.33	
Open circuit voltage (V)	21.60	21.60	21.60	
Short circuit current (A)	3.05	3.36	3.60	
Cell Efficiency (%)	16.50%	16.75%	17.00%	
FF (%) ≥74%				
Maximum system voltage (V)	715V		
Temperature Range		`-40℃ to +85℃		
Power tolerance (%)		±5%		
Standard Test Conditions	1000	1000W/m2 , AM1.5 , 25°C		
LI I I I I I I I I I I I I I I I I I I				

Mechanical Characteristics

Solar cell	Mono	Mono	Mono	
Number of cells (Pcs)	36(4*9) / 72(4*18)			
Size of module (mm)	810*534*35mm			
Weight per piece (kg)	6.5			
Front Glass	3.2 mm tempered glass			
Surface Maximum Load Capacity	60m/s(200kg/sq.m)			
Allowable Hail Load	steel ball	fall down from	1m height	
Frame	Anodized aluminium alloy			
Junction Box Type	IP65 rated			
Temperature coefficients				
Nominal Operating Cell Temperature		45±2°C		
Temperature coefficients of Voc (%)		β -2.2mV/°C		
Temperature coefficients of Pm (%)		γ -0.55%/°C		
Temperature coefficients of Im (%)		α 0.03%/°C		
Temperature coefficients of Vm (%)		β -2.2mV/°C		